

GEN 718 Welding Wire and Rod

GEN 718 is used for welding nickel-chromium-niobium-molybdenum alloy (ASTM B637 and AMS 5589) to itself. The weld metal will age harden on heat treatment; its mechanical properties depend on the post weld heat treatment.

CONFORMANCES

AWS A5.14	:	ERNiFeCr-2
ASME SFA-5.14	:	ERNiFeCr-2
UNS	:	N07718

AWS CHEMICAL COMPOSITION (TYPICAL)

%C	%Cr	%Ni	%Mo	%Ti	%Fe	%Mn	%B
0.08 max. 0.045	17.0 – 21.0 18.5	50.0 – 55.0 53.8	2.80 – 3.30 2.90	0.65 – 1.15 0.95	Rem. 17.7	0.35 max. 0.05	0.006 max. 0.003
%Si	%P	%S	%Cu	%Al	%Nb+Ta	Total Others	
0.35 max. 0.06	0.015 max. 0.007	0.015 max. 0.001	0.30 max. 0.10	0.20 – 0.80 0.55	4.75 – 5.50 5.18	0.50 max.	

TYPICAL WELD METAL MECHANICAL PROPERTIES (AS-WELDED)

Tensile Strength	:	125,000 psi	862 MPa
Yield Strength	:	85,000 psi	586 MPa
Elongation	:	28%	

TYPICAL WELDING PARAMETERS*

Process	Diameter		Voltage	Amperage	Gas/Flux
TIG (GTAW)	1/16	1.6 mm	14 – 18	90 – 130	100% Ar
	3/32	2.4 mm	15 – 20	120 – 180	100% Ar
	1/8	3.2 mm	15 – 20	150 – 220	100% Ar
MIG (GMAW)	.035"	0.9 mm	26 – 30	150 – 200	75% Ar – 25% He
	.045"	1.1 mm	28 – 32	180 – 230	75% Ar – 25% He
Sub Arc (SAW)	.093"	2.4 mm	28 – 30	275 – 350	
	.125"	3.2 mm	29 – 32	350 – 450	

*All parameters are suggested as basic guidelines only and will vary depending on joint design, number of passes and other factors.

<p>IMPORTANT: SPECIAL VENTILATION AND/OR EXHAUST REQUIRED</p> <p>BEFORE USE, READ AND UNDERSTAND THE SAFETY DATA SHEET (SDS) FOR THIS PRODUCT AND SPECIFIC INFORMATION PRINTED ON THE PRODUCT CONTAINER.</p>

The contents of this document are presented for informational purposes only and while every effort has been made to ensure their accuracy, they are not to be construed as guarantees, express or implied, regarding the products or services described herein or their use or applicability. The user must fully evaluate every process and application in all aspects.